

## TEST REPORT

No. : SZIN2505001086PL01\_EN

Date : 2025-05-21

Page: 1 of 3



CUSTOMER NAME: AKUDECO  
ADDRESS: PO BOX 51, 5060 AB, OISTERWIJK

Sample Name : WPC OUTDOOR WALL PANEL

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*

SGS Ref. No. : GZIN2505000791CM01\_EN  
Date of Receipt : 2025-05-09  
Testing Period : 2025-05-09 ~ 2025-05-21  
Test result(s) : For further details, please refer to the following page(s)  
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for  
SGS-CSTC Standards Technical  
Services Co., Ltd. ShenZhen Branch.

*Jessie*

Jessie Ho  
Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

Room 101-801, Plant 4 & Room 101, Plant 2 & Room 101, Plant 3 & Room 301-501, Plant 3, Jiangshao (Bantian) Industrial Plant Area, No. 430, Jihua Road, Bantian Community, Bantian Street, Longgang District, Shenzhen, Guangdong, China 518129 [www.sgs.com](http://www.sgs.com)  
中国·广东·深圳市龙岗区坂田街道坂田社区吉华路430号江潮（坂田）工业厂区厂房4号101-901、2号101、3号301-501 邮编:518129 t(86-755) 25328673 sgs.china@sgs.com

## TEST REPORT

No. : SZIN2505001086PL01\_EN


Date : 2025-05-21

Page: 2 of 3

### Summary of Results:

No.	Test Item	Test Method	Result
1	Flexural Properties	EN 15534-1:2014+A1:2017 Section 7.3.2 and Annex A	See results

### Original Sample Photo:



## TEST REPORT

No. : SZIN2505001086PL01\_EN

Date : 2025-05-21

Page: 3 of 3

Test Item: Flexural Properties

Sample Description: See photo

Test Method: EN 15534-1:2014+A1:2017 Section 7.3.2 and Annex A

Test Condition:

Specimen: 400 mm×220 mm×26 mm

Testing speed: 19.24mm/min

Span: 300 mm (Provided by client)

Moment of inertia: 144268 mm<sup>4</sup>

Test result:

Test Item	Test Result
Flexural strength	24.9 MPa
Flexural modulus	3227 MPa

Note: The test method was carried out by SGS-CSTC Standards Technical Services Co., Ltd.

Guangzhou Branch.

Appendix information:

The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.

\*\*\*\*\*End of report\*\*\*\*\*